

	NOV SARA ENGINEERING SPECIFICATION	
	SECTION SES 26 – 720 B	FMC TECHNOLOGIES
	ISSUE "A" REV "0"	DOC. No. M30200, REV "H"
	EFF. DATE: 09.08.2009	Page 1 of 3

MATERIAL SPECIFICATION AISI SS316 STAINLESS STEEL

1.0 PURPOSE

- 1.1** It is the purpose of this material specification to list in concise form of the material requirement for AISI SS 316 bar stock, forgings, centrifugal castings, mill shapes and Ring Joint Gaskets.
- 1.2** Product forms covered by this specification are Rolled Ring or Ring forgings for Gaskets.
- 1.3** This material specification is intended to aid the purchasing department in procuring and the vendor in supplying a material which meets the needs of its intended use, and the quality control department in the inspection and release of incoming material.
- 1.4** It is the responsibility of raw material/metal supplier/machined parts supplier of carbon, low alloy and martensitic stainless steel to have practices and procedures in place to assure that raw materials/parts delivered to FMC do not have excessive amounts of residual magnetism. Excessive residual magnetism is defined as greater than 3 gauss. Residual magnetism can occur due to factors such as lifting with magnets, magnetic particle inspection or stray welding current. The supplier's procedures/testing methods will be subject to verification during supplier audits.
- 1.5** The raw material supplier shall assure that FMC does not receive material with greater than background level of radioactivity.

2.0 REQUIREMENTS

- 2.1** The requirements of specification S.E.S. 26-590 shall apply in addition to the following specific requirements.
- 2.1.1** **Chemical composition:** Chemical composition limits are listed below. An analysis of each heat of steel is made by the manufacturer, preferably from a ladle sample taken at or near the time of pouring. The listed elements shall be reported in weight percent. Reporting of residual elements is not required, but total residuals must not exceed 1%.

	NOV SARA ENGINEERING SPECIFICATION	
	SECTION SES 26 - 720 B	FMC TECHNOLOGIES
	ISSUE "A" REV "0"	DOC. No. M30200, REV "H"
	EFF. DATE: 09.08.2009	Page 2 of 3

ELEMENTS	COMPOSITION RANGE (%)
Carbon (C)	0.08 (max.)
Manganese (Mn)	2.00 (max.)
Silicon (Si)	1.00 (max.)
Sulphur (S)	0.03 (max.)
Phosphorus (P)	0.045 (max.)
Nickel (Ni)	10.0-14.0
Chromium (Cr)	16.0-18.0
Molybdenum (Mo)	2.00-3.00
Iron (Fe)	Balance

2.1.2 Elements that are not included in the application material specification but that may have been intentionally added by the mill are limited as follows:

ELEMENTS	COMPOSITION RANGE (%)
Vanadium (V)	0.08 (max.)
Aluminum (Al)	0.055 (max.)
Nitrogen (N)	0.010 (max.)
Hydrogen (H)	0.010 (max.)
Niobium(Columbium)+Titanium +Vanadium	0.12 (max.)
Boron	0.0005 (max.)

2.1.3 Mechanical Properties: Mechanical property requirements are listed below. Each heat shall be tested and the listed mechanical properties shall be reported.

<u>MECHANICAL PROPERTIES</u>	<u>RANGE</u>
TENSILE STRENGTH, PSI	75,000 (517 MPa) Min. *
YLELD STRENGTH, PSI	30,000 (207 MPa) Min. *
ELONGATION IN 2" Gage Length	40 % Min. *
REDUCTION IN AREA	50% Min. *
BRINELL HARDNESS	237 BHN Max. *

* These properties are not required for ring gaskets. Ring Gaskets shall have a maximum Hardness of 83 HRB.

	NOV SARA ENGINEERING SPECIFICATION		
	SECTION SES 26 – 720 B	FMC TECHNOLOGIES	
	ISSUE “A” REV “0”	DOC. No. M30200, REV “H”	
	EFF. DATE: 09.08.2009	Page	3 of 3

2.1.4 HEAT TREATMENT: - Heat treatment

PROCESS	ATMOSPHERE/MEDIA	TEMPERATURE	TIME AT TEMPERATURE
Normalizing	Air	1900-2050 °F (1040-1120 °C)	1/2 hour per inch of maximum through Thickness. One hour minimum
Quenching	Water	100 °F (38 °C) max at the start of quench	120°F Max. at the completion of the quench

Note: Maximum holding time shall not exceed Four times (5X) the maximum holding time. In all case, holding time shall not start until parts or materials have reached specified heat treatment temperature. The 5X rule does not apply to the separate QTC (e.g. ER 5”)

3. DOCUMENTATION REQUIRED:-

3.1 Each shipment shall be accompanied by material certifications for each lot of material, certifications must be positively relatable to the lot of material represented.

3.2 Recheck of Chemical properties to be carried out by NOV SARA.