

|   |                                    |                          |
|---|------------------------------------|--------------------------|
|  | NOV SARA ENGINEERING SPECIFICATION |                          |
|   | SECTION SES 26 – 723               | Doc. No. M40411, REV "H" |
|   | ISSUE "B", REV "0"                 |                          |
|   | EFF. DATE: 09-08-2010              | Page 1 of 3              |

**MATERIAL SPECIFICATION**  
**FOR INCOLOY 625 SOLUTION ANNEALED CONDITION**

### **1.0 PURPOSE**

- 1.1** It is the purpose of this material specification to list in concise form of the material requirement for INCOLOY 625 (UNS N06625).
- 1.2** This material specification is intended to aid the purchasing department in procuring and the vendor in supplying a material which meets the needs of its intended use, and the quality control department in the inspection and release of incoming material.

### **2.0 REQUIREMENTS**

- 2.1** The requirements of specification SES 26-590, SES 26-740 & SES 26-744 shall apply in addition to the following specific requirements.
- 2.2** It is the responsibility of raw material/metal supplier/machined parts supplier of carbon, low alloy and martensitic stainless steel to have practices and procedures in place to assure that raw materials/parts delivered to FMC do not have excessive amounts of residual magnetism. Excessive residual magnetism is defined as greater than 3 gauss. Residual magnetism can occur due to factors such as lifting with magnets, magnetic particle inspection or stray welding current. The supplier's procedures/testing methods will be subject to verification during supplier audits.
- 2.3** The raw material supplier shall assure that FMC does not receive material with greater than background level of radioactivity.

**3.0 Chemical composition:** Chemical composition limits are listed below. An analysis of each heat of steel is made by the manufacturer, preferably from a ladle sample taken at or near the time of pouring. The listed elements shall be reported in weight percent. Reporting of residual elements is not required, but total residuals must not exceed 1%.

|   |                                    |                          |
|---|------------------------------------|--------------------------|
|  | NOV SARA ENGINEERING SPECIFICATION |                          |
|   | SECTION SES 26 – 723               | Doc. No. M40411, REV "H" |
|   | ISSUE "B", REV "0"                 |                          |
|   | EFF. DATE: 09-08-2010              | Page 2 of 3              |

| ELEMENTS             | COMPOSITION RANGE (%) |
|----------------------|-----------------------|
| Carbon (C)           | 0.10 (max.)           |
| Manganese (Mn)       | 0.50 (max.)           |
| Silicon (Si)         | 0.50 (max.)           |
| Sulfur (S)           | 0.015 (max.)          |
| Phosphorus (P)       | 0.015 (max.)          |
| Nickel (Ni)          | Balance               |
| Chromium (Cr)        | 20.0 – 23.0           |
| Molybdenum (Mo)      | 8.0 – 10.0            |
| Aluminum (Al)        | 0.40 (max.)           |
| Titanium (Ti)        | 0.40 (max.)           |
| Columbium & Tantalum | 3.15 – 4.15           |
| Cobalt (Co)          | 1.00 (max.)           |
| Niobium (Nb)         | 3.15 – 4.15           |
| Iron (Fe)            | 5.0 (max.)            |

**3.1.1** Elements that are not included in the application material specification but that may have been intentionally added by the mill are limited as follows:

| ELEMENTS                              | COMPOSITION RANGE (%) |
|---------------------------------------|-----------------------|
| Vanadium (V)                          | 0.08 (max.)           |
| Aluminum (Al)                         | 0.055 (max.)          |
| Nitrogen (N)                          | 0.010 (max.)          |
| Hydrogen (H)                          | 0.010 (max.)          |
| Niobium(Columbium)+Titanium +Vanadium | 0.12 (max.)           |
| Boron                                 | 0.0005 (max.)         |

**4.0 Mechanical Properties:** Mechanical property requirements are listed below. Each heat shall be tested and the listed mechanical properties shall be reported.

| <u>MECHANICAL PROPERTIES</u> | <u>RANGE</u>                 |
|------------------------------|------------------------------|
| YLELD STRENGTH *             | 60-70 ksi (414-483 MPa) Min. |
| ROCKWELL HARDNESS            | 95 HRB (209BHN) Max.         |

\*Yield strengths outside of this range will not be accepted.

**5.0 HEAT TREATMENT:** -

|   |  |   |        |
|---|--|---|--------|
|  |  | <b>NOV SARA ENGINEERING SPECIFICATION</b> |        |
| SECTION SES 26 – 723  |  | Doc. No. M40411, REV "H"                  |        |
| ISSUE "B", REV "0"  |  |   |        |
| EFF. DATE: 09-08-2010   |  | Page                                      | 3 of 3 |

| PROCESS   | ATMOSPHERE/MEDIA | TEMPERATURE                               | TIME AT TEMPERATURE   |
|---|------------------|---|---|
| Annealing   | Solution         | 1950-2200 °F<br>(1066-1204 °C)            | ½ hour per inch of maximum through thickness. One hour minimum. |
| <b><u>Note:</u> Maximum holding time shall not exceed Five times (5X) the minimum holding time. In all case, holding time shall not start until parts or materials have reached specified heat treatment temperature. The 5X rule does not apply to the separate QTC (e.g. ER 5")</b> |                  |   |   |
| Quenching   | Water            | 100 °F (38 °C) Max at the start of quench | 120°F (49 °C) Max. at the completion of the quench              |

**6.0 MARKING:** Each Piece or component shall be identified with the heat number or traceability marked on the exterior with low stress dot stamps. When used for Ring Gaskets, each piece shall also be stamped with the designation "I - 625".

#### **7.0 DOCUMENTATION REQUIRED:-**

**7.1** Each shipment shall be accompanied by material certifications for each lot of material, certifications must be positively relatable to the lot of material represented

**7.2** Recheck of Chemical properties to be carried out by NOV SARA.