

SARA SAE ENGINEERING SPECIFICATION

SECTION SES 26-601A

ISSUE "B"

Rev.: "3"

EFF. DATE :07.08.2017

Page 1 of 3

EN-19 LOW ALLOY STEEL 75,000 PSI MINIMUM YIELD

1.0 SCOPE

- 1.1 EN - 19 low alloy steel heat-treated to 75,000 PSI minimum yield strength
- 1.2 Product forms covered by this specification are bar and mill shapes.

2.0 REQUIREMENTS

- 2.1 The requirements of specification S.E.S. 26-590 shall apply in addition to the following specific requirements.

2.1.a) Chemical composition: Chemical composition limits are listed below. An analysis of each heat of steel be made by the manufacturer, preferably from a ladle sample taken at or near the time of pouring. The listed elements shall be reported in weight percent. Reporting of residual elements is not required, but total residuals must not exceed 1%.

ELEMENT	COMPOSITION	ELEMENT	COMPOSITION
CARBON (C)	0.35 - 0.45	SILICON (Si).	0.10- 0.35
MANGANESE (Mn).	0.50 – 0.80	CHROMIUM	0.90-1.50
PHOSPHORUS (P).	0.050 max.	MOLYBDENUM	0.20 – 0.40
SULPHUR (S).	0.050 max.		

2.1.b) Mechanical Properties: Mechanical property requirements are listed below. Each heat shall be tested and the listed mechanical properties shall be reported.

MECHANICAL PROPERTIES	RANGE
TENSILE STRENGTH	95,000 PSI (655 MPa) Min.
YIELD STRENGTH	75,000 PSI (517 MPa) Min.



	SARA SAE ENGINEERING SPECIFICATION			
	SECTION SES 26-601A			
	ISSUE "B"		Rev.: "3"	
	EFF. DATE :07.08.2017		Page	2 of 3

2.1.c) Melt practice: The steel shall be made by the electric furnace process with subsequent vacuum treatment (EFVD). Steel made by vacuum induction melting (VIM) or vacuum arc remelting (VAC), or electroslag remelting (ESR) or electric arc furnace (EAF) shall also be acceptable.

2.1.d) Condition: All product shall be normalized (N) then quenched (Q) and tempered (T) (N+Q&T), except that normalizing shall not be required for the bar stock with a diameter of 8" or less.

2.1.e) Heat Treatment :

PROCESS	ATMOSPHERE/MEDIA	TEMPERATURE	TIME AT TEMPERATURE
Normalized	Air or Nitrogen	1600 °F (871 °C) minimum.	½ hour per inch of maximum through thickness. One hour minimum.

Still air cool to below 400 °F (204 °C) before further processing


Austenitize (See note 2.1.e.1)	Air or Nitrogen	1575 °F (857 °C) minimum	½ hour per inch of maximum through thickness. One hour minimum.
--------------------------------------	-----------------	-----------------------------	---

Quench	Water	100 ° F (38 °C) maximum before quenching 120 ° F (49 °C) maximum after quenching	
	Polymer	50 ° F (10 °C) minimum before quenching (See note 2.1.f.2)	
	Oil	-----	

Tempering - Air or Nitrogen

BHN	HRC	Elongation	Temp.	Soaking
				Hardness
207-237	16-22	22	650° C	3/4hour per inch of maximum through thickness. One hour Minimum.
235-285	22-30	18	630° C	
302-345	30-35	15	540° C Min.	
375-415	40-45	10	315°C - 330°C	
423-485	45-50	8	300°C - 315°C	



	SARA SAE ENGINEERING SPECIFICATION		
SECTION SES 26-601A			
ISSUE "B"	Rev.: "3"		
EFF. DATE :07.08.2017	Page	3 of 3	

Note 2.1.e.1: The Austenitizing temperature shall be less than the normalizing temperature.

Note 2.1.e.2: The minimum start temperature of 50 °F (10 °C) for oil and polymer Quenchant shall be followed except when a lower minimum start temperature is permitted for a specific quenchant by the quenchant manufacturer. The start temperature shall be documented for all products.

2.1.f) Continuous Furnace Heat Treatment: Continuous furnace heat treatment shall be an acceptable alternative to conventional batch-type heat treatment for bars with diameters of 8 inches (203mm) or less. The following parameters shall be followed and reported in accordance with SES-26-590.

Minimum bar temperature exiting final zone of austenitizing furnace	1525 °F (829 °C)
Minimum time in austenitizing furnace	5 minutes (see note 2.1.g.1)
Minimum bar temperature exiting final zone of temperature furnace	1150 °F (621 °C)
Minimum time in tempering furnace	5 minutes (see note 2.1.g.1)
Minimum temperature of quench water	120 °F (49 °C)

Note 2.1.f.1: Continuous furnaces consist of several different temperature zones through which the bar travels. The zone temperatures in the austenitizing furnace are chosen so as to heat the bar to a completely austenitic in a relatively short time. The bar is then spray quenched before entering the tempering. Zone temperatures in the tempering furnace are chosen to produce the desired tempering effect, again in a relatively short time. The time spent in the austenitizing and tempering furnaces depends primarily upon the length of the furnace and the travel speed. Travel speed varies according to the diameter of the bar. The time in each furnace shall be sufficient to attain the desired mechanical properties and to produce a microstructure to that obtained in a conventional quench-and-temper heat treatment.

