

	SARA SAE ENGINEERING SPECIFICATION	
	SECTION SES 26-724	Doc. No. M41104, REV "D"
	ISSUE "B",	REV "1"
	EFF. DATE: 20.10.2011	Page 1 of 3

## MATERIAL SPECIFICATION INCOLOY 825

### **1.0 PURPOSE**

- 1.1 It is the purpose of this material specification to list in concise form of the material requirement for INCOLOY 825.
- 1.2 This material specification is intended to aid the purchasing department in procuring and the vendor in supplying a material which meets the needs of its intended use, and the quality control department in the inspection and release of incoming material.

### **2.0 REQUIREMENTS**

- 2.1 The requirements of specification SES 26-590, SES 26-740 & SES 26-744 shall apply in addition to the following specific requirements.
- 2.2 It is the responsibility of raw material/metal supplier/machined parts supplier of carbon, low alloy and martensitic stainless steel to have practices and procedures in place to assure that raw materials/parts delivered to FMC do not have excessive amounts of residual magnetism. Excessive residual magnetism is defined as greater than 3 gauss. Residual magnetism can occur due to factors such as lifting with magnets, magnetic particle inspection or stray welding current. The supplier's procedures/testing methods will be subject to verification during supplier audits.
- 2.3 The raw material supplier shall assure that FMC does not receive material with greater than background level of radioactivity.

**3.0 Chemical composition:** Chemical composition limits are listed below. An analysis of each heat of steel is made by the manufacturer, preferably from a ladle sample taken at or near the time of pouring. The listed elements shall be reported in weight percent. Reporting of residual elements is not required, but total residuals must not exceed 1%.



**SARA SAE ENGINEERING SPECIFICATION**

SECTION SES 26 - 724	Doc. No. M41104, REV "D"
ISSUE "B",	REV "1"
EFF. DATE: 20.10.2011	Page 2 of 3

ELEMENTS	COMPOSITION RANGE (%)
Carbon (C)	0.05 (max.)
Manganese (Mn)	1.00 (max.)
Silicon (Si)	0.50 (max.)
Sulphur (S)	0.03 (max.)
Nickel (Ni)	38.0 – 46.0
Chromium (Cr)	19.5 – 23.5
Molybdenum (Mo)	2.5 – 3.5
Aluminum (Al)	0.20 (max.)
Titanium	0.6 – 1.2
Copper (Cu)	1.5 – 3.0
Iron (Fe)	Balance

**3.1** Elements that are not included in the application material specification but that may have been intentionally added by the mill are limited as follows:

ELEMENTS	COMPOSITION RANGE (%)
Vanadium (V)	0.08 (max.)
Aluminum (Al)	0.055 (max.)
Nitrogen (N)	0.010 (max.)
Hydrogen (H)	0.010 (max.)
Niobium(Columbium)+Titanium +Vanadium	0.12 (max.)
Boron	0.0005 (max.)

**3.1.1 Mechanical Properties:** Mechanical property requirements are listed below. Each heat shall be tested and the listed mechanical properties shall be reported. Mechanical properties shall be obtained by from coupon or block 2"x2"x8" taken from the same heat, reduced by forging and processed with the product they represent.

MECHANICAL PROPERTIES	RANGE
TENSILE STRENGTH, PSI	75,000 (517 MPa) Min.
YIELD STRENGTH, PSI	30,000 - 55,000 (207- 380 MPa)
ELONGATION IN 2" Gauge Length	30 % Min.
ROCKWELL HARDNESS	83 HRB (160BHN) Max.



	SARA SAE ENGINEERING SPECIFICATION		
	SECTION SES 26 - 724	Doc. No. M41104, REV "D"	
	ISSUE "B",	REV "1"	
	EFF. DATE: 20.10.2011	Page	3 of 3

**4.0 HEAT TREATMENT:** -

PROCESS	ATMOSPHERE/MEDIA	TEMPERATURE	TIME AT TEMPERATURE
Annealing	Air	1700-1900 °F (927-1038 °C)	½ hour per inch of maximum through Thickness. One hour minimum.
Quenching	Water	100 °F (38 °C) Max at the start of quench.	120°F (49 °C) Max. at the completion of the quench.

**4.1 HARDNESS: 83 HRB Max.**

**5.0 MARKING:** Each Piece or component shall be identified with the heat number or traceability marked on the exterior with low stress dot stamps. When used for Ring Gaskets, each piece shall also be stamped with the designation "I - 825".

**6.0 DOCUMENTATION REQUIRED:-**

- 6.1 Each shipment shall be accompanied by material certifications for each lot of material, certifications must be positively relatable to the lot of material represented
- 6.2 Recheck of Chemical properties to be carried out by SARA SAE.

