

 Sara Sae	SARA SAE ENGINEERING SPECIFICATION		
	Section: SES 26 – 749	Doc. No. "M11801" Rev "D"	
	Issue: "A",	Rev. No.: "1"	
	Eff. Date: 20.10.2011	Page	1 of 2

MATERIAL SPECIFICATION
FOR AISI 1006-1010 SOFT IRON

1.0 SCOPE

1.1 Product forms covered by this specification are closed die, Open die and ring forgings or fusion welding.

2.0 REQUIREMENTS

- 2.1** The requirements of specification SES 26-590, SES 26-740 & SES 26-744 shall apply in addition to the following specific requirements.
- 2.2** It is the responsibility of raw material/metal supplier/machined parts supplier of carbon, low alloy and martensitic stainless steel to have practices and procedures in place to assure that raw materials/parts delivered to SARA SAE do not have excessive amounts of residual magnetism. Excessive residual magnetism is defined as greater than 3 gauss. Residual magnetism can occur due to factors such as lifting with magnets, magnetic particle inspection or stray welding current. The supplier's procedures/testing methods will be subject to verification during supplier audits.
- 2.3** The raw material supplier shall assure that SARA SAE does not receive material with greater than background level of radioactivity.

3.0 Chemical composition: Chemical composition limits are listed below. An analysis of each heat of steel shall be made by the manufacturer, preferably from a ladle sample taken at or near the time of pouring. The listed elements shall be reported in weight percent.

ELEMENTS	COMPOSITION RANGE (%)
Carbon (C)	0.10 (max)
Manganese (Mn)	0.40 (max)
Silicon (Si)	0.34 (max)
Sulphur (S)	0.050 (max)
Phosphorus (P)	0.040 (max)

3.1 Elements that are not included in the application material specification but that may have been intentionally added by the mill shall be reported and are limited as follows. Total residuals must not exceed 1%.

ELEMENTS	COMPOSITION RANGE (%)
Vanadium (V)	0.08 (max)
Aluminum (Al)	0.055 (max)
Nitrogen (N)	0.010 (max)
Hydrogen (H)	0.010 (max)
Niobium(Columbium)+Titanium +Vanadium	0.12 (max)
Boron	0.0005 (max)



	SARA SAE ENGINEERING SPECIFICATION		
Section: SES 26 - 749	Doc. No. "M11801" Rev "D"	Issue: "A",	Rev. No.: "1"
Eff. Date: 20.10.2011		Page	2 of 2

4.0 Mechanical Properties: Mechanical property requirements are listed below. Each heat shall be tested and the listed mechanical properties shall be reported.

MECHANICAL PROPERTIES	RANGE
TENSILE STRENGTH *	340 MPa (49313 PSI)
YIELD STRENGTH *	285 MPa (41336 PSI)
ELONGATION *	20 %
HARDNESS	56 HRB (101 HB) Max.

* These properties are not required for Ring Gaskets

5.0 HEAT TREATMENT

PROCESS	ATMOSPHERE/MEDIA	TEMPERATURE	TIME AT TEMPERATURE
Annealing	Air	1550 °-1650 °F (845° - 900 °C)	1/2 hour per inch of maximum thickness. One hour minimum.
<p>Note: Maximum holding time shall not exceed Five times (5X) the minimum holding time. In all cases, holding time shall not start until parts or materials have reached specified heat treatment temperature. The 5X rule does not apply to the separate QTC (e.g. ER 5")</p>			
Furnace cool to below 1300 °F (700 °C)			

6.0 MARKING: Each Piece or component shall be identified with the heat number or traceability marked on the exterior with low stress dot stamps. When used for Ring Gaskets, each piece shall also be stamped with the designation "D-4".

7.0 DOCUMENTATION REQUIRED:-

- 7.1 Each shipment shall be accompanied by material certifications for each lot of material, certifications must be positively relatable to the lot of material represented
- 7.2 Recheck of Chemical properties to be carried out by SARA SAE.

