

|                                                                                   |                                           |                    |
|-----------------------------------------------------------------------------------|-------------------------------------------|--------------------|
|  | <b>SARA SAE ENGINEERING SPECIFICATION</b> |                    |
|                                                                                   | <b>Section: SES 26 – 803</b>              |                    |
|                                                                                   | <b>ISSUE “A”</b>                          | <b>REV “0”</b>     |
|                                                                                   | <b>EFF. DATE: 18.05.2016</b>              | <b>Page 1 of 3</b> |

**MATERIAL SPECIFICATION FOR AISI 8620 LOW ALLOY STEEL**

| Rev | Reason of Change | Date       | Made By | Reviewed By | Approved By | Status   |
|-----|------------------|------------|---------|-------------|-------------|----------|
| 0   |                  | 18-05-2016 | MN      | AS          | KKD         | Released |

|                                                                                   |                                           |                    |
|-----------------------------------------------------------------------------------|-------------------------------------------|--------------------|
|  | <b>SARA SAE ENGINEERING SPECIFICATION</b> |                    |
|                                                                                   | <b>Section: SES 26 – 803</b>              |                    |
|                                                                                   | <b>ISSUE “A”</b>                          | <b>REV “0”</b>     |
|                                                                                   | <b>EFF. DATE: 18.05.2016</b>              | <b>Page 2 of 3</b> |

## **MATERIAL SPECIFICATION FOR AISI 8620 LOW ALLOY STEEL**

### **1.0 PURPOSE**

- 1.1** It is the purpose of this material specification to list in concise form of the material requirement for AISI 8620 bar stock, forgings, castings.
- 1.2** This material specification is intended to aid the purchasing department in procuring and the vendor in supplying a material which meets the needs of its intended use, and the quality control department in the inspection and release of incoming material.

### **2.0 REQUIREMENTS**

- 2.1** The requirements of specification SES 26-590, SES 26-740 & SES 26-744 shall apply in addition to the following specific requirements.
- 2.2 Chemical composition:** The listed elements shall be reported in weight percent. Reporting of residual elements is not required, but total residuals must not exceed 1%.

|             | <b>AISI 8620</b> |
|-------------|------------------|
| Carbon      | .18 to .23       |
| Manganese   | .70 to .90       |
| Phosphorous | .025 max.        |
| Sulfur      | .025 max.        |
| Silicon     | .15 to .35       |
| Chromium    | .40 to .60       |
| Nickel      | .40 to .70       |
| Molybdenum  | .15 to .25       |

### **3.0 Mechanical Properties:**

The mechanical properties must be obtained from specimens machined and tested in accordance with ASTM A370. The specimens must be from the same heat as the intended part and heat treated in the same cycle. Shipment requiring more

|                                                                                   |                                           |                |               |
|-----------------------------------------------------------------------------------|-------------------------------------------|----------------|---------------|
|  | <b>SARA SAE ENGINEERING SPECIFICATION</b> |                |               |
|                                                                                   | <b>Section: SES 26 – 803</b>              |                |               |
|                                                                                   | <b>ISSUE “A”</b>                          | <b>REV “0”</b> |               |
|                                                                                   | <b>EFF. DATE: 18.05.2016</b>              | <b>Page</b>    | <b>3 of 3</b> |

than one heat treatment lot will require specimens and complete identification from each lot. The following minimum requirements must be met:

|                                  |         |
|----------------------------------|---------|
| Tensile strength (psi)           | 110,000 |
| Yield strength (psi)             | 85,000  |
| Elongation, 2" gauge length, (%) | 17      |
| Reduction of area, %             | 35      |
| Brinell Hardness, HB             | 207-237 |
| Rockwell "C" Hardness (HRC)      | 17-22   |

#### **4.0 HEAT TREATMENT: -**

| <b>PROCESS</b>                                                                  | <b>ATMOSPHERE/MEDIA</b> | <b>TEMPERATURE</b>                     | <b>TIME AT TEMPERATURE</b>                                            |
|---------------------------------------------------------------------------------|-------------------------|----------------------------------------|-----------------------------------------------------------------------|
| <b>Normalized</b>                                                               | Air                     | 1598 °F – 1697 °F<br>(870 °C – 925 °C) | 30 Minutes / Inch of T, Minimum<br>Time is 30 Minutes.                |
| Still air cool to below 400 degrees F (204 degrees C) before further processing |                         |                                        |                                                                       |
| <b>Austenitize</b>                                                              | Air                     | 1562 °F - 1652 °F<br>(850 °C – 900 °C) | 30 Minutes / Inch of T, Minimum<br>Time is 30 Minutes.                |
| <b>Quench</b>                                                                   | Oil                     | 104 °F (40 °C) - 158 °F (70 °C)        |                                                                       |
| <b>Temper</b>                                                                   | Air                     | 1100 °F – 1256 °F<br>(593 °C – 680 °C) | 1 hour per inch of maximum<br>through thickness. One-hour<br>Minimum. |

**Note:** Maximum holding time shall not exceed Five times (5X) the maximum holding time. In all case, holding time shall not start until parts or materials have reached specified heat treatment temperature. The 5X rule does not apply to the separate QTC (e.g. ER 5")

#### **5.0 DOCUMENTATION REQUIRED:-**

Each shipment shall be accompanied by material certifications for each lot of material, certifications must be positively relatable to the lot of material represented.  
Recheck of Chemical properties to be carried out by Sara Sae.