



SARA SAE PRIVATE LIMITED

Management System Document Control Cover Sheet

Document Title	Ref. No.	Revision No.
Procedure for Magnetic Particle Testing	SSE-QAD-MT-1/97	5

	Name	Position	Signature	Date
Prepared by	JAGMOHAN SINGH	MANAGER QA		08/11/2015
Reviewed by	MADAN LAL SHARMA	ASNT NDT LEVEL III RT, UT, MT, PT. File No 67185		08/11/2015
Approved by	S. DHAWAN	MANAGING DIRECTOR		08/11/2015

Issued To		
Name:	Signature:	Date:

Document Control Stamp (Valid only if in red)



This document is the property of SARA SAE PRIVATE LIMITED and is confidential.
The document may not be reproduced, issued or removed without written authority from Management.

Revision Status

Revision No.	Effective Date	Description / Summary of Revision
0	10/11/2012	Initial Issue
1	10.02.2009	Change of name of company "Sara Sae" to "NOV Sara "
2	21.10.2011	Change of name of company "NOV Sara" to "SARA SAE"
3	10.11.2012	Clauses identified with "line on left" amended
4.	25.04.2014	Compliances with FMC Doc. No. Q01114.
5.	08.11.2015	Compliances with FMC Doc. No. Q01114 Rev. AA, API 6A, API 16A, API 16C

Contents

- i. Purpose
- ii. Scope
- iii. Definitions
- iv. References
- v. Responsibilities
- vi. Procedure Instructions
- vii. Annexure A

1. PURPOSE

- 1.1 The purpose of this procedure is to establish the requirements for magnetic particle inspection of ferromagnetic materials.
- 1.2 This procedure provides a system of general conditions and specific instructions as an aid to qualified personnel required to perform magnet particle inspection, using A.C /HWDC Electromagnets.

2. SCOPE

- 2.1 This procedure gives the methods, techniques, quality, and reporting requirements necessary for the magnetic particle inspection of ferromagnetic materials.
- 2.2 This procedure covers the magnetic particle inspection of ferromagnetic materials including fusion welded butt joints in plate and pipe welds, using the magnetic flow technique with A.C /HWDC. Electromagnet yokes. **Prods are not permitted on well fluid surface or sealing surface.**
- 2.3 This procedure covers requirement of **PSL 3**, all accessible wetted surface and all accessible sealing surfaces of each finished part shall be magnetic Particle inspected after final heat treatment and final machining operations. All magnetic Particle Examination shall use the **wet Fluorescent Method**.
- 2.4 This is the Company approved procedure and shall be adhered to at all times except where the Client or Contract specifies other requirements.

3. REFERENCES

- 3.1 ASME V - Nondestructive Examination.
- 3.2 API 1104 - Welding of Pipelines and Related Facilities.
- 3.3 ASME VIII - Rules for the Construction of Pressure Vessels.
Division 1.
- 3.4 ASMEB31.3 - Chemical Plant and Petroleum Refinery Piping.
- 3.5 AWS D1.1 - Structural Welding Code.
- 3.6 SARA SAE Quality assurance Manual
 - 3.6.1 SDP-22-004 Personal Certification
 - 3.6.2 SDP-27-009 Control of Non-conforming Products
- 3.7 American Petroleum Institute (API)
 - 3.7.1 Specification 6A "Specification for Well Head and Christmas Tree Equipment"
 - 3.7.2 Specification 7K "Specification for "Drilling Well services"
 - 3.7.3 Specification 11E "Specification for Pumping Units"
 - 3.7.2 Specification 16A "Specification for Drill through Equipment"
 - 3.7.3 Specification 16C "Specification for Choke and kill system"
 - 3.7.4 Specification 16D "Specification for Control System for Drilling Well Control equipment"
- 3.8 American Society for Testing of Metals:
 - 3.8.1 ASTM E-709, "Standard Guide for Magnetic Particle Testing"
- 3.9 FMC Q01114 Rev. AA: Magnetic Particle Examination of Ferromagnetic Materials and Welds

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 3 of 13

4. RESPONSIBILITIES

- 4.1 The President/Manager QA shall be responsible for ensuring that the necessary resources are available for the requirements of this procedure to be carried out.
- 4.2 Operations Management/**NDT Level III** shall be responsible for ensuring that the requirements of this procedure are fully implemented at all times.
- 4.3 Employees involved in the implementation of this procedure shall be responsible for adherence to the requirements stated within.

5. DEFINITIONS

- 5.1 Company – SARASAE PRIVATE LIMITED
- 5.2 Client - Those companies, Organizations or Individuals to which the company is contracted to provide Services.
- 5.3 Contract - The form of agreement for the provision of the Services to the Client by the Company.
- 5.4 Services - All things provided under the Contract including all activities to be carried out by the company for the client.

6. PROCEDURE

6.1 PERSONNEL QUALIFICATIONS

- 6.1.1 The NDT Inspector shall be trained, qualified and certified to a minimum ASNT (third party) Level II, reference to SNT-TC-1 A, "Recommended Practice for Non-Destructive Testing Personnel Qualification and Certification", and SARA written Practice **SES-26-7430R** international equivalent, i.e., PCN, CSWIP in the applicable NDT method.

6.2 EQUIPMENT AND TESTING MEDIA

- 6.2.1 An A.C. /DC electromagnet yoke or Permanent Magnet having a minimum lifting power of 4.5kg (AC) / 18kg (DC) of ferrite steel with the poles set at the intended test spacing shall be used.
- 6.2.2 However, for A.C. electromagnet Yoke use on as required basis, i.e. call – out basis, a magnetic lifting power function check shall be carried – out prior to use and documented using the same form as in 6.2.1 indicating the intended purpose.
- 6.2.3 Testing media from a recognized manufacturer shall be used.
- 6.2.4 Recognized manufacturers include Magnaflux and Chemetall or equivalent.
- 6.2.5 Unacceptable system performance verification tests shall result in re – inspection of all parts examined since the last acceptable verification.
- 6.2.6 Wet magnetic particle Suspension shall be prepared as specified in SE 709 section 8. Exxon Isopar M or equivalent light petroleum distillate may be used as a vehicle to suspend the magnetic particle. **Smooth test surface require wetting agent than rough surfaces.** The particle concentration of the suspension must be checked prior to each shift by the following method:

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 4 of 13

- 6.2.6.1 Circulate the suspension a minimum of thirty (30) minutes to assure thorough mixing of particles.
- 6.2.6.2 Place a sample of the suspension in a 100ml Centrifuge tube and allow it to settle for minimum of 60 minutes, preferably on non-vibrating surfaces.
- 6.2.6.3 The settled particles should appear as a solid layer. The acceptable particle concentration is 0.1 to 0.4 ml, by volume for fluorescent particles and 1.2 to 2.4 ml per 100 ml for non - fluorescent particle.
- 6.2.6.4 Magnetized or contaminated particles will appear as loose agglomerated in the suspension. Particles suspension having this appearance will be discarded and replaced with new particle suspension in a cleaned tank.
- 6.2.6.5 The temperature of the particle solution shall not exceed 43 C and will be within +/- 14C of the part being examined.

6.2.6.6 Required Inspection Intervals are:

Item (ASTM E709)	Interval
Visible Light Intensity (7.1.1)	Weekly
Ambient Light Intensity (7.1.1)	Weekly
Black Light Intensity (7.1.2)	Daily
Light Meter Checks (20.3.7)	6 months
Gauss Meter (20.3.6)	6 months
System Performance (20.8)	Daily
Wet Particle Concentration (20.6)	8 hours, or every shift change
Wet Particle Contamination (20.6.4)	Weekly

6.3 GENERAL PROCEDURE:

- 6.3.1 If a part or piece holds a residual magnetism field from a previous magnetization that will interfere with the examination, the part must be demagnetized.
- 6.3.2 All surfaces within 25mm of the area to be examined shall be free of grease, clean, dry, and free of irregularities which could mask, or be confused with an indication. **As welded, as rolled, as cast or as forged surfaces are generally accepted, but if surface is non uniform, interpretation may be difficult because of mechanical entrapment of magnetic particles, questionable indications should be re cleaned and re - examined.**
- 6.3.3 **If a coating/painting is left on the area to be examined that has thickness greater than 0.05mm it must be demonstrated that discontinuity can be detected through the maximum thickness required.**
- 6.3.4 **Small openings and oil holes leading to obscure passage or cavities should be plugged or masked with suitable non abrasive material which can be easily removed.**
- 6.3.5 Only solvent-based cleaner and remover from an approved manufacturer shall be used for cleaning prior to application of the white contrast paint.
- 6.3.6 Drying of the pre-cleaned surfaces shall be accomplished by normal evaporation. A minimum of five (5) minutes shall be allowed before applying of white contrast paint.
- 6.3.7 The temperature of the surface being examined shall not exceed 57°C throughout the examination period.
- 6.3.8 Field Indicators:
 - 6.3.8.1 Pie Field Indicator: Suitable field strength and direction is clearly indicated by a line of magnetic particle across the copper face.
 - 6.3.8.2 Linear Slotted Shims: Suitable field strength is indicated by a clear indication on the strip. Linear slots must be lined up perpendicular to the field direction and multiple strips (minimum 2) used to verify multidirectional magnetizing processes.
 - 6.3.8.3 Circular Slot Shims: Suitable field strength is indicated by either a particle indication on opposite sides of the circle for single directional magnetization.

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015

- 6.3.9 White contrast paint shall be applied in controlled passes at a distance of 15 – 30 cm to give an opaque coating which provides adequate contrast with the test surface.
- 6.3.10 Adequate time will be allowed for the paint to dry before examination.
- 6.3.11 A Burmah Castrol Strip shall be placed aligned parallel with the direction of any discontinuities on the test surface.
- 6.3.12 The inspected area shall be considered to be not greater than the circle inscribed between the pole pieces.
- 6.3.13 All inspection shall be conducted with sufficient overlap to assure 100% coverage and at least two separate examinations shall be performed on each area. During the second inspection, the lines of magnetic flux shall be approximately perpendicular to those used during the first examination.
- 6.3.14 The inspected area shall be free from interfering debris.
- 6.3.15 The area under inspection shall be illuminated by daylight or artificial light from either a normal tungsten filament lamp or a fluorescent tube, to a level of illumination not less than 100 FTC (1076 Lux) so as to enable a proper evaluation to be made of the indications revealed. The viewing conditions shall be such that no glare will be experienced during inspection of the component.
- 6.3.16 Fluorescent Particle Examination shall be conducted in a darkened area (Max Light intensity 2 FTC or 21.5 Lux) using filtered black light. The Black light intensity at the examination surface shall not be less than $1000\mu\text{W}/\text{cm}^2$.
- 6.3.17 Reflectors and filters should be checked and if necessary cleaned prior to use. Cracked or broken filters shall be replaced immediately
- 6.3.18 When using mercury vapor bulb, allow black light to warm up for a minimum of five minutes prior to its use. Prior to the start of test 5 minutes period shall be allowed for technician eyes to adjust to dark viewing. Photosensitive glasses are not allowed.
- 6.3.19 Post cleaning to remove residual magnetic particle solution is required on all parts. Particles are to be removed by use of compressed air, wiping with solvent, or other suitable method which will not interfere with subsequent requirements.
- 6.3.18 The examination area should be kept free of interfering debris. If fluorescent materials are involved, the area should also be kept free of fluorescent objects not related to the part/piece being examined.

6.4 MT Inspection Procedure :

Wet Fluorescent Method:

This Method utilizes fluorescent magnetic Particle suspended in a vehicle (water or petroleum distillate) that are sprayed, flowed or poured on the surface to be examined. Fluorescent magnetic Particles will glow a bright greenish – yellow when viewed under a black light.

- 6.4.1 Select a Yoke Suitable for the configuration to be examined.
- 6.4.2 Applicable light intensity should meet the criteria of clause 6.3.18.
- 6.4.3 Surface Temperature should meet the criteria of clause 6.3.6
- 6.4.4 Magnetization: Each Part must be magnetized in two directions, approximately 90 degree to each other. Place yoke perpendicular to or parallel to the weld or other area to be examined.
- 6.4.5 Turn on the magnetizing force for the yoke and at the same time apply the particle suspension by spraying, flowing or pouring on the area to be examined.
- 6.4.6 While the magnetizing force is still applied, evaluate the surface of examination for any indications. Mark any relevant indications observed
- 6.4.7 Repeat the examination above with the yoke positioned at 90 deg. to the first examination.

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 6 of 13

6.5 EVALUATION OF INDICATIONS

- 6.5.1 All indications shall be investigated to the extent that the Inspector can evaluate such indications in terms of the applicable acceptance criteria.
- 6.5.2 **Indications shall be clearly marked for identification and disposition.**
- 6.5.3 Relevant indications are those which result from mechanical discontinuities.
- 6.5.4 **Relevant Indication - An indication with the major dimension greater than 1/16" (1.6mm).**
- 6.5.5 Such indications shall include the following:-
Cracks.
Linear indications – those indications in which the length is more than **three (3)** times the width.
Rounded indications or indications which are circular or elliptical with the length less than **three (3)** times the width.
- 6.5.6 Non-relevant indications include:-
Localized surface imperfections, such as may occur from machining marks or surface conditions. These are not relevant to the detection of unacceptable discontinuities and shall not be reported.
- 6.5.7 Any questionable or doubtful indications shall be retested to verify whether or not actual discontinuities are present.
- 6.5.8 As a guide, this can be achieved by using either a fluorescent tube of 80W at a distance of approximately 1m or a tungsten filament pearl lamp of 100W at a distance of approximately 0.2m.
- 6.5.9 If any indications are believed to be non-relevant on the basis that they are not associated with a surface rupture (i.e magnetic permeability variations, nonmetallic stringers), they shall be examined by LPT methods, or removed and re-inspected, to confirm their non-relevancy.

6.6 ACCEPTANCE STANDARDS

- 6.6.1 The acceptance standards for the interpretation of items inspected shall be Client requirements or the Contract Document.
- 6.6.2 If no Client requirements or Contract Document are available the international specification relevant to the work scope shall be used.
- 6.6.3 **Annexure B shall be referred for all acceptance criteria.**

6.7 EXAMINATION OF REPAIRS

- 6.7.1 Repairs shall be re-examined by the same procedure used for the original examination.

6.8 POST INSPECTION CLEANING& DEMAGNETIZATION

- 6.8.1 When required, post inspection cleaning shall be accomplished to remove residual inspection materials by flushing with solvent then finally wiping with rags.
- 6.8.2 In the case of using HWDC, Demagnetization is necessary until the residual field is less than 3Guass which is verified by a Gauss meter.
- 6.8.3 Demagnetization can be done by energizing the magnet and pulling away from the specimen (Implying Reverse the current /Reduce the field)

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 7 of 13

6.9 REPORTING

- 6.9.1 A Magnetic Particle examination report is required and will contain the following minimum information. Sample format of report as per Annexure A:
- 6.9.2 Report Number
- 6.9.3 Part Number and Revision Level
- 6.9.4 Part Description
- 6.9.5 **Client Procedure number with revision.**
- 6.9.6 **Lightning Equipment.**
- 6.9.7 Weld Number and Welders Symbol
- 6.9.8 Traceability code
- 6.9.9 Date of examination
- 6.9.10 Scope of examination
- 6.9.11 Examination parameter
- 6.9.12 Type and manufacturer of the equipment, Model, serial number and calibration date.
- 6.9.13 Quantity examined
- 6.9.14 Results of examination reject able, and recordable indication
- 6.9.15 Technician name and certification level and type
- 6.9.16 Particles used

6.10 SAFETY

- 6.10.1 Care shall be exercised during inspection with due regard to the fact that the inspection media may have relatively toxic and flammable properties.
- 6.10.2 Manufacturer's recommendations shall be followed at all times.
- 6.10.3 Smoking is prohibited while performing magnetic particle inspection.
- 6.10.4 Controlled conditions shall be established for correct disposal of pressurized aerosol cans.
- 6.10.5 Suitable precautions should be taken when using electrical equipment to avoid arcing, sparking or localized over-heating.
- 6.10.6 **Safety Precaution shall be taken from the ignition of a petroleum distillate bath.**
- 6.10.7 **Care shall be taken from slipping on a wetted floor with a magnetic suspension.**

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 8 of 13

Annexure A
Report
Formats



Sara Sae Pvt Ltd

WORKSHEET FOR MAGNETIC PARTICLE TESTING

Report No.:	Doc No: Annex 'A' of SSE/QAD/M Rev: 5																						
Job Ref.:	S	NS																					
Worksheet Issue Date:	Page 1 of 4																						
<p>Customer : _____</p> <p>Address : <input checked="" type="checkbox"/> Required by customer <input type="checkbox"/> Not required by customer</p> <p>Project : _____</p> <p>Location of Test : _____ Date of Test : _____</p> <p>INFORMATION PROVIDED BY THE CUSTOMER</p> <p>Material Description : <input checked="" type="checkbox"/> Steel <input type="checkbox"/> Other : _____</p> <p>Weld Configuration : _____</p> <p>Test Standard/Specification No. : _____</p> <p>Acceptance Standard : _____</p> <p><input type="checkbox"/> Others : _____</p> <p>Surface Condition : <input checked="" type="checkbox"/> As welded <input type="checkbox"/> As ground <input type="checkbox"/> Others : _____</p> <p>Material Specification : _____</p> <p>Welding Process : <input type="checkbox"/> MMA <input type="checkbox"/> TIG <input type="checkbox"/> Others : _____</p> <p>Acceptance Level : _____</p> <p>Heat Treatment : _____</p> <p>LABORATORY INFORMATION</p> <p>Test Procedure No.:</p> <p>Magnetising Equipment <input checked="" type="checkbox"/> Permanent Magnet <input type="checkbox"/> A.C./H.V.D.C. Yoke</p> <p>Test Technique : Wet Fluorescent Technique</p> <p>Demagnetization Required : _____</p> <p>Black Magnetic Ink : _____</p> <p>Welding Gauge : _____</p> <p>Steel Rule : _____</p> <p>Measuring Tape : _____</p> <p>Test Temperature : 250°C</p> <p>Poles Spacing : _____</p> <p>Viewing Condition : <input type="checkbox"/> Day Light <input type="checkbox"/> Background Light <input type="checkbox"/> UV Light <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> <input type="checkbox"/> Others : _____</p> <p>Test Restriction : <input type="checkbox"/> None <input type="checkbox"/> Others : _____</p> <p>Calibration / Equipment Checking / Viewing Condition Check Record</p> <p>Equipment Checking at Laboratory :-</p> <table style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 60%;"></th> <th style="width: 20%; text-align: center;">Acceptable</th> <th style="width: 20%; text-align: center;">Unacceptable</th> <th style="width: 10%;"></th> </tr> </thead> <tbody> <tr> <td>* Lifting Power Check 4.5 kg for A.C. Yoke</td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;">Equipment No.:</td> </tr> <tr> <td>* Lifting Power Check 18 kg for Permanent Magnet / DC Yoke</td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;">Equipment No.:</td> </tr> </tbody> </table> <p>Equipment Checking at Site :-</p> <table style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 60%;">Magnetic Flux Direction Check</td> <td style="width: 20%; text-align: center;"><input type="checkbox"/></td> <td style="width: 20%; text-align: center;"><input type="checkbox"/></td> <td style="width: 10%; text-align: center;">Equipment No.:</td> </tr> <tr> <td>White Light Level Check</td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;"><input type="checkbox"/></td> <td style="text-align: center;">Equipment No.:</td> </tr> </table> <p>Remarks : 1) <input type="checkbox"/> O : Tick an Comply. 2) * Delete Inappropriate</p> <p>Tested by : _____ Checked by : _____</p> <p>Name / Signature : _____ / _____ Qualification : _____</p>					Acceptable	Unacceptable		* Lifting Power Check 4.5 kg for A.C. Yoke	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:	* Lifting Power Check 18 kg for Permanent Magnet / DC Yoke	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:	Magnetic Flux Direction Check	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:	White Light Level Check	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:
	Acceptable	Unacceptable																					
* Lifting Power Check 4.5 kg for A.C. Yoke	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:																				
* Lifting Power Check 18 kg for Permanent Magnet / DC Yoke	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:																				
Magnetic Flux Direction Check	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:																				
White Light Level Check	<input type="checkbox"/>	<input type="checkbox"/>	Equipment No.:																				

WORKSHEET FOR MAGNETIC PARTICLE TESTING

Report No.:

Job Ref:

Doc no: Annex 'A' of SSE/QAD/MT, U/97

W. L. S. and D. C.

Rev:

Page 2 of 4

WORKSHEET FOR MAGNETIC PARTICLE TESTING

Report No.:

Job Ref.:

Doc. no. Annex 'A' of SSE/QADM

Rev. 5

Worksheet Issue Date :

Page 3 of 4

Sketch Sheet : (Location of Test, Legs Position and coverage)

Sketch Sheet : (Location of Test, Legs Position and coverage)	
Tested by :	
Name / Signature : _____ / _____ Qualification :	

WORKSHEET FOR MAGNETIC PARTICLE TESTING

Report No.:

Job Ref.:

Doc. no: Annex 'A' of SSE/QAD/MT-1/97

Rev. : 5

Worksheet Issue Date :

Page 4 of 4

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015

Page 12 of 13

Annexure B
Acceptance Criteria

API 6A/API 16C

Surface NDE

The following acceptance criteria apply:

- no relevant indication with a major dimension equal to or greater than 5 mm ($\frac{3}{16}$ in);
- no more than ten relevant indications in any continuous 40 cm^2 (6 in^2) area;
- four or more relevant indications in a line separated by less than 1,6 mm ($\frac{1}{16}$ in) (edge to edge) are unacceptable;
- no relevant indications in pressure contact sealing surfaces.

Weld NDE

- no relevant linear indication;
- no rounded indication greater than 3 mm ($\frac{1}{8}$ in) for welds whose depth is 16 mm ($\frac{5}{8}$ in) or less; or 5 mm ($\frac{3}{16}$ in) for welds whose depth is greater than 16 mm ($\frac{5}{8}$ in).

API 16 A

Surface other than pressure – contact (metal – to – metal) sealing surface:

- No relevant indication with a major dimension equal to or greater than 5 mm (0,2 in).
- No more than ten relevant indications in any continuous 10 cm^2 ($2,5\text{ in}^2$) area.
- Four or more relevant indications in a line separated by less than 1,5 mm (0,06 in) (edge to edge) are unacceptable.

Pressure – contact (metal – to – metal) sealing surface:

There shall be no relevant indications in the pressure-contact (metal-to-metal) sealing surfaces.

Weld NDE (Pressure containing welds, repair and weld overlay)

- no relevant linear indications;
- no rounded indications greater than 3 mm (0,125 in) for welds whose depth is 16 mm (0,63 in) or less or 5 mm (0,2 in) for welds whose depth is greater than 16 mm (0,63 in).

Document Title: Magnetic Particle Testing	Revision: 5
Technical Procedure No.: SSE-QAD-MT-1/97	Date: 08/11/2015 Page 13 of 13