

Sample Result Name	Type	Measure Date Time	Recalculation Date Time	Origin
9565 (318456) R-45,R-73,BX-154,R-54,R-53,BX-158, R-46	Unknown	Wednesday, June 11, 2014	2:29:50 PM	Measured
Method Name	Method Version	Operator Name	Check Type	Check Status
Fe-30-MO		SARA SAE	None	Not Used
Grade Verification Name	Grade Verification Similarity	Correction Type	Type Corr Sample Name	Grade Search Name
	0	None		
Grade Search Similarity	Type	Status	Outlier Removal	
0	None	Not Used		

Sample Name	Grade
9565 (318456) R-45,R-73,BX-154,R-54,R-53,BX-158, R-46	

	C Conc %	Si Conc %	Mn Conc %	P Conc %	S Conc %	Cr Conc %	Mo Conc %	Ni Conc %	Al Conc %	Co Conc %	Cu Conc %	Nb Conc %	Ti Conc %	V Conc %	W Conc %	Pb Conc %	Sn Conc %	As Conc %	Zr Conc %
2	0.081	0.37	0.49	0.024	0.021	0.14	<0.003	0.045	0.47	<0.005	0.085	<0.005	0.018	<0.002	<0.040	0.068	0.008	0.022	0.007
3	0.069	0.27	0.39	0.022	0.023	0.11	<0.003	0.048	0.38	<0.005	0.10	<0.005	0.009	<0.002	<0.040	0.042	0.005	0.010	0.007
4	0.084	0.23	0.27	0.021	0.017	0.086	0.019	0.059	0.25	<0.005	0.12	<0.005	0.004	<0.002	<0.040	0.027	0.007	<0.005	0.004
Rep	0.078	0.29	0.38	0.022	0.020	0.11	0.008	0.051	0.37	<0.005	0.10	<0.005	0.011	<0.002	<0.040	0.046	0.006	0.012	0.006
Min Cal	0.006	0.005	0.004	0.003	0.002	0.005	0.003	0.005	0.003	0.005	0.002	0.005	0.0010	0.002	0.040	0.010	0.002	0.005	0.003
Mean	0.078	0.29	0.38	0.022	0.020	0.11	<0.002	0.051	0.37	<0.0004	0.10	<0.028	0.011	<0.0003	<0.040	0.046	0.006	0.012	0.006
Max Cal	3.00	5.04	18.12	0.18	0.30	36.00	10.20	55.2	6.24	21.60	7.44	3.60	3.60	12.00	7.32	0.13	0.27	0.13	0.19
	Ca Conc %	B Conc %	Fe Conc %																
2	>0.016	0.010	98.1																
3	>0.016	0.007	98.4																
4	>0.016	0.005	98.7																
Rep	>0.016	0.007	98.4																
Min Cal	0.0005	0.0005																	
Mean	>0.066	0.007	98.5																
Max Cal	0.016	0.025																	

on in
1008
Copy

