

**BSL****SPECTRO LAB**

&
METALLURGICAL TESTING CENTRE
 (NABL ACCREDITED LAB)
 (An Unit of BSL Castings Pvt. Ltd.)

WORKS & OFFICE :
 PLOT NO. 263, SECTOR-24
 FARIDABAD-121005 (INDIA)
 Fax No. : +91-129-4065535
 Ph. No. : 4065531, 4065532
 E-mail : castings@bsltd.net

TEST REPORT

BSL/SPECTRO/5.10F-01/01/00

To : M/s. Nov Sara India (P) Ltd.
 7/1, Pritam Road, Unit - II
 Dehra Dun - 248001

Report No. 115000 D.O.T. : 21.02.2009

Ref. No. Nil D.O.R. : 21.02.2009

Sample Description Sample No. - 2711A, Heat No. - 810464, RCS - 90mm

J.O. No. : 35539

RESULTS**Chemical Analysis**

Sample ID: J.O.No. - 35539/1

By Spectrometer (ASTM E1507;1998)

| <u>Element</u> | <u>%</u> |
|----------------|----------|
| Carbon | 0.073 |
| Silicon | 0.152 |
| Sulphur | 0.011 |
| Phosphorus | 0.019 |
| Manganese | 0.421 |
| Nickel | 0.017 |
| Chromium | 0.007 |
| Molybdenum | 0.002 |
| Vanadium | 0.001 |
| Copper | 0.000 |
| Tungsten | 0.000 |
| Cobalt | 0.001 |
| Aluminium | 0.013 |
| Titanium | 0.000 |
| Magnesium | 0.000 |
| Iron | 99.27 |

Checked By



Authorised Signatory
 (Q.M. / T.M.)

1. The result listed refer only to the tested samples and applicable parameters, Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. This report can not be used as an evidence in a court of law.
4. Samples will be destroyed after 15 days.
5. Any Complaints about this report should be communicated within 7 days of issue of this report.
6. This report shall not be reproduced except in full, without the written permission of the Laboratory.
7. *Not Covered under NABL Scope.

