

BSL**SPECTRO LAB****METALLURGICAL TESTING CENTRE**

(An Unit of BSL Castings Pvt. Ltd.)

(NABL ACCREDITED LAB)

TEST REPORT**WORKS & OFFICE :**

PLOT NO. 263, SECTOR-24

FARIDABAD-121005 (INDIA)

Fax No. : +91-129-4065535

Ph. No. : 4065531, 4065532

E-mail : castings@bsltd.net

CERTIFICATE NO.
T - 1452 & T - 1453

BSL/SPECTRO/5.10F-01/01/00

Issued to : M/s. Nov Sara India (P) Ltd.
7/1, Pritam Road, Unit - II
Dehra Dun - 248001

Report No. 110719

D.O.T. : 12.12.2008

Ref. No. NIL

D.O.R. : 09.12.2008

Sample Description

Sample No. - 2241, Heat No. - 810853, 6" Male 200

J.O. No. : 34248

RESULTS**Chemical Analysis**

Sample ID; J.O.No. - 34248

By Spectrometer (ASTM E1507;1998)

<u>Element</u>	<u>%</u>
Carbon	0.186
Silicon	0.201
Sulphur	0.011
Phosphorus	0.022
Manganese	0.567
Nickel	0.014
Chromium	0.013
Molybdenum	0.000
Vanadium	0.000
Copper	0.003
Tungsten	0.000
Cobalt	0.001
Aluminium	0.021
Titanium	0.000
Iron	98.95

Checked By

Authorised Signatory
(Q.M. / T.M.)

- Note : 1. The result listed refer only to the tested samples and applicable parameters, Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. This report can not be used as an evidence in a court of law.
4. Samples will be destroyed after 15 days.
5. Any Complaints about this report should be communicated within 7 days of issue of this report.
6. This report shall not be reproduced except in full, without the written permission of the Laboratory.
7. *Not Covered under NABL Scope.

BSL**SPECTRO LAB****METALLURGICAL TESTING CENTRE**

(An Unit of BSL Castings Pvt. Ltd.)

(NABL ACCREDITED LAB)

TEST REPORT**WORKS & OFFICE :**PLOT NO. 263, SECTOR-24
FARIDABAD-121005 (INDIA)

Fax No. : +91-129-4065535

Ph. No. : 4065531, 4065532

E-mail : castings@bsltd.net

CERTIFICATE NO.
T - 1452 & T - 1453

BSL/SPECTRO/5.10F-01/01/00

Issued to :

M/s. Nov Sara India (P) Ltd.
7/1, Pritam Road, Unit - II
Dehra Dun - 248001

Report No. 110720

D.O.T. : 12.12.2008

Ref. No. Nil

D.O.R. : 09.12.2008

Sample Description

Sample No. - 2241, Heat No. - 810853, 6" Male 200

J.O. No. : 34248

TEST RESULTS

Tensile Strength - N/mm ² (Psi)	524.54 (76078.23)
Yield Stress - N/mm ² (Psi)	349.69 (50718.34)
Elongation (%)	32.00
R.A. (%)	57.29
Hardness BHN	137

Protocol Used : ASTM A-370

Checked By

Authorized Signatory
(Q.M. / T.M.)

- Note : 1. The result listed refer only to the tested samples and applicable parameters, Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. This report can not be used as an evidence in a court of law.
4. Samples will be destroyed after 15 days.
5. Any Complaints about this report should be communicated within 7 days of issue of this report.
6. This report shall not be reproduced except in full, without the written permission of the Laboratory.
7. *Not Covered under NABL Scope.