



SPAN FORGING PVT. LTD.

Mfrs. of : Steel Forgings, CNC Turned Components, Centrifugal Casting of alloy steel

Mobile : 9999986702

9999986704

9810010535

Works : Village Tatarpur (Near Prithla) Teh. & Distt. Palwal

E-mail : spanforging@rediffmail.com

TEST REPORT

Date.....

Ref. No.

Issued to: M/s SARA SAE(P)Ltd.Unit-II
A/2Sara Ind.Estate Ltd.Chak-
rata Road,Selaqui,Dehradun.

Report No.

1242

D..O.T.

22/3/2012

D..O.R

22/3/2012

Sample Description

Dia-56

Sample No.

7482

Heat No.

D-2127

RESULTS

Chemical Analysis
By Spectrometer

Element

%

Carbon	0.0466
Silicon	0.458
Sulphur	0.0128
Phosphorus	0.0263
Manganese	1.06
Nickel	10.41
Chromium	16.41
Molybdenum	2.08
Vanadium	0.0539
Copper	0.359
Niobium/Columbium	0.0261
Cobalt	0.221
- Aluminium	0.0144
Titanium	0.0163
Iron	68.70

Checked By
Arun Mishra



Authorised Signatory
(Q.M / T.M)

1. The result listed refer only to the tested samples and applicable parameters. Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. The report can not be used as an evidence in a court of law.
4. Samples will be destroyed after 15 days.
5. Any Complaints about this report should be communicated within 7 days of issue of this report.
6. This report shall not be reproduced except in full, without the written permission of the Laboratory.
7. *Not Covered under NABL Scope.



MATERIAL TEST CERTIFICATE

TC NO-KSL-3373/11-12	Date :	23.03.2012	Buyer:- M/S SARA SAE PVT LTD, DEHRADUN
Heat No. D -2127			Delivery:- M/S GEE GEE INDUSTRIES, JALANDHAR
Specification:- AISI 316	P.O. No.:	B/KES/0147/11 Dated 18.02.12	Invoice No: 1016 Date 23.03.2012

SL. NO.	ITEM DESCRIPTION & DRAWING NO.	QUANTITY NOS
1	Round Dia 56 MM	80
	Grade Color Code: Pink	
	Heat No. Color Code: White	

CHEMICAL COMPOSITION

PERCENT	C	Mn	Si	P	S	Cr	Ni	Mo	Cu	Ti	Al	V	
AS PER SPEC.	Min. (%)					16.00	10.00	2.00					
	Max. (%)	0.080	2.00	1.00	0.045	0.030	18.00	14.00	3.00				
	Actual Value	0.057	1.15	0.44	0.031	0.015	16.52	10.11	2.19				

HEAT TREATMENT

Condition	Temp. C	Soaking Time Hrs.	Cooling Medium

PHYSICAL PROPERTIES

MECHANICAL PROPERTIES	Y.S. N/mm ²	U.T.S. N/mm ²	ELONG % GL mm	REDN IN AREA %	BEND	HARDNESS BHN	IMPACT (Joules)
AS PER SPEC.	Min.						
	Max.						
	Actual Value						

We hereby certify that the items mentioned above have been tested and inspected in our presence and are found to be in accordance with the drawing, specifications, and purchase order.

91.04X80 \Rightarrow 7283

REMARK

The Steel has been made by Electric Furnace which is fully killed by Al & Si. It has fine grain structure.

Sign of the Inspecting Officer



Sign of the Chief of Quality Control

Registered Office :

G & JU – 26/1, Pitampura, Telefax : + (91) 11 27343847
Delhi-110090 (INDIA) Fax : + (91) 11 27343857

Works :

A – 350, Phase-I, Riico Industrial Area,
Bhiwadi-301012, Rajasthan (INDIA)

Phone : + (91) 1493 220142 * :WWW.KSL.IN