

Heat No - H8

 6 Dia - 5mm  
 Colou - Purpul  
 01C

Sample Result Name	Type	Measure Date Time	Recalculation Date Time	Origin	Method Name	Method Version	Operator Name	Correction Type	Type Corr Sample Name
SARA	Unknown	5/16/2014 4:44:40 PM	5/16/2014 4:45:25 PM	Measured	Fe-30-MO		8613	None	
Check Type	Check Status	Grade Verification Name		Grade Verification Similarity		Grade Search Name		Grade Search Similarity	
None	Not Used			0 %				0 %	
Sample Name	Grade Nom	Grade							
	SARA								

**Elements**      **Conc.**

Meas.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co
	%	%	%	%	%	%	%	%	%	%
	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.
1	0.11	0.42	1.15	0.012	0.023	15.94	2.23	10.40	0.023	0.15
2	0.10	0.43	1.18	0.012	0.015	15.98	2.16	10.38	0.021	0.15
3	0.10	0.42	1.16	0.012	0.016	16.06	2.18	10.38	0.015	0.15
4	0.10	0.42	1.17	0.013	0.018	16.14	2.20	10.34	0.021	0.15
Cal. Min	0.006	0.005	0.004	0.003	0.002	0.005	0.003	0.005	0.003	0.005
$\langle x \rangle$	0.10	0.42	1.17	0.012	0.018	16.03	2.19	10.37	0.020	0.15
Cal. Max	3.00	5.04	18.12	0.18	0.30	36.00	10.20	55.2	6.24	21.60
Mean	0.10	0.42	1.17	0.012	0.018	16.03	2.19	10.37	0.020	0.15
SD	0.004	0.005	0.010	0.0006	0.003	0.089	0.030	0.026	0.003	0.0005
	0.08	0.42	1.18	0.040	0.025	16.39	2.02	10.06		

Meas.	Cu	Nb	Ti	V	W	Pb	Sn	As	Zr	Ca
	%	%	%	%	%	%	%	%	%	%
	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.	Conc.
1	0.41	0.049	0.019	0.058	0.082	0.013	0.012	<0.005	<0.003	0.001
2	0.41	0.046	0.025	0.055	0.072	0.012	0.013	<0.005	<0.003	0.002
3	0.41	0.047	0.018	0.056	0.081	0.012	0.013	<0.005	<0.003	0.001
4	0.42	0.051	0.016	0.058	0.094	0.012	0.013	<0.005	<0.003	0.001
Cal. Min	0.002	0.005	0.0010	0.002	0.040	0.010	0.002	0.005	0.003	0.0005
$\langle x \rangle$	0.41	0.048	0.020	0.056	0.082	0.012	0.013	<0.005	<0.003	0.001
Cal. Max	7.44	3.60	3.60	12.00	7.32	0.13	0.27	0.13	0.19	0.016
Mean	0.41	0.048	0.020	0.056	0.082	0.012	0.013	<0.019	<0.002	0.001
SD	0.005	0.002	0.004	0.001	0.009	0.0003	0.0003	0.0000	0.0000	0.0004

0.42

### Test Certificate

TC No: 01	Invoice No: 34	Date: 09-05-2014
Customer Name and Address:		Sara Sae Pvt. Ltd.
Behjnd Radha Swami Satsang Ghar, G.T. Road, Goraya, (Punjab)		
Supply condition: As rolled round		

### Chemical Analysis


Elements	C	Mn	P	Si	S	Cr	Mo	Ni	Heat No	PC S.	Weight	Grade	Size	Colour
Result	.071	1.22	.031	.41	.019	16.04	2.03	10.05	H-3	29	2565	SS316	56mm	Blue
Result	.066	1.23	.027	.46	.011	16.14	2.02	10.02	H-4	29	3285	SS316	40mm	Yellow
Result	.074	1.22	.031	.42	.016	16.05	2.01	10.00	H-5	30	1330	SS316	40mm	Green
Result	.072	1.14	.029	.37	.013	16.02	1.99	10.01	H-6	14	825	SS316	45mm	White
Result	.072	1.23	.029	.42	.012	16.37	2.03	10.01	H-7	18	1595	SS316	50mm	Red
Result	.073	1.28	.029	.44	.011	16.10	2.03	10.04	H-8	6	530	SS316	50mm	Pink
Result	.073	1.28	.029	.44	.011	16.10	2.03	10.04	H-8	12	1055	SS316	60mm	Pink

#### Remarks:

1. Manufacturing Route: Induction Furnace
2. Material is free from residual radioactive elements.
3. Lead not added during manufacturing.

We are confirming that test result findings are correct and results are as per standard/customers requirement.

On in SS316  
 as per 26-720  
 Lijahetut

  
Quality Incharge