

BSL**SPECTRO LAB****METALLURGICAL TESTING CENTRE**(A Unit of BSL Castings Pvt. Ltd.)
(NABL ACCREDITED LAB)**&****TEST REPORT**

WORKS & OFFICE :
 PLOT NO. 263, SECTOR-24,
 FARIDABAD - 121 005 (INDIA)
 Ph. No. : 0129-4189800
 FAX No. : +91-129-4065535
 E.mail : castings@bsltd.net

CERTIFICATE NO.
T - 1452 & T - 1453

BSL/SPECTRO/5.10F-01/01/00

Issued to :	M/s. Sara Sae (P) Ltd. 7/1, Pritam Road, Unit - II Dehra Dun - 248001	Report No.	210839	D.O.T. :	09.03.2013
		Ref. No.	Nil	D.O.R. :	08.03.2013
		Sample No. - 8311, Heat No. - R-737, Round Dia - 56.0mm			J.O. No. : 64975

Sample Description. :

RESULTS

Chemical Analysis (Fe Base - SS) Sample ID: J.O.No. - 64975/2
 Protocol : ASTM E 1086:2008 (By O.E.S)

<u>Element</u>	<u>%</u>
Carbon	0.050
Silicon	0.506
Sulphur	0.013
Phosphorus	0.029
Manganese	1.326
Nickel	10.19
Chromium	16.64
Molybdenum	2.091
Copper	0.352
Tungsten	0.052
Cobalt	0.197
# Niobium	0.032
# Titanium	0.011

Checked By



Authorised Signatory
 (Q.M. / T.M.)

Note :

1. The result listed refer only to the tested samples and applicable parameters, Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. *Not Covered under NABL Scope.
4. This report can not be used as an evidence in a court of law.
5. Samples will be destroyed after 15 days.
6. Any Complaints about this report should be communicated within 7 days of issue of this report.
7. This report shall not be reproduced except in full, without the written permission of the Laboratory.
8. # Results found outside the range of NABL accredited scope.

GE 1017

TEST CERTIFICATE

TC No.: P-141

Date : 12.03.2013

INVOICE NO: 472

Customer Name & Address :

M/S SARA SAE P.LTD
DEHRADUN

Supply Condition :

AS ROLLED

CHEMICAL ANALYSIS IN PERCENTAGE

H.NO	Grade	C	Si	Mn	P	S	Cr	Mo	Ni	N	Size	Pc	Weight	Colour Code
R-736	AISI-316	.074	.51	1.51	.035	.018	16.41	2.08	10.08	.0576	56MM	40	4140	BLUE
R-737	AISI-316	.061	.49	1.39	.038	.017	16.62	2.08	10.13	.0548	56MM	40	4135	BLUE
R-738	AISI-316	.055	.49	1.48	.037	.015	16.68	2.08	10.11	.0588	56MM	20	2075	BLUE

Remarks :

Manufacturing Route: Electric Induction Furnace
 Ultrasonic testing as per ASTM A 388
 Material is free from residual radioactive elements.
 Lead not added during manufacturing.

We are Confirming that the Test Certificate findings are Correct & Results are as per Standard / Customer's Requirements.

Lab Incharge



Quality Controller