

BSL**SPECTRO LAB**CERTIFICATE NO.
T - 1452 & T - 1453**METALLURGICAL TESTING CENTRE**(A Unit of BSL Castings Pvt. Ltd.)
(NABL ACCREDITED LAB)**&****TEST REPORT****WORKS & OFFICE :**PLOT NO. 263, SECTOR-24,
FARIDABAD - 121 005 (INDIA)
Ph. No. : 0129-4189800
FAX No. : +91-129-4065535
E.mail : castings@bsltd.net

BSL/SPECTRO/5.10F-01/01/00

Issued to :	M/s. Sara Sae (P) Ltd. 7/1, Pritam Road, Unit - II Dehra Dun - 248001	Report No.	203461	D.O.T. :	02.11.2012
Sample Description. :	Sample No. - 8075, Round Dia - 56.0mm Heat No. - T-101	Ref. No.	Nil	D.O.R. :	01.11.2012
				J.O. No. :	62931

RESULTS

Chemical Analysis (Fe Base - SS)
Protocol : ASTM E 1086:2008-(By O.E.S)

Sample ID; J.O.No. - 62931/4


<u>Element</u>	<u>%</u>
Carbon	0.066
Silicon	0.409
Sulphur	0.017
Phosphorus	0.037
Manganese	0.993
Nickel	10.23
Chromium	16.15
Molybdenum	2.015
Copper	0.392
Tungsten	0.047
Cobalt	0.178
# Niobium	0.030
Titanium	0.020

Checked By

BSL & METALLURGICAL TESTING CENTRE
263, SECTOR-24, FARIDABAD
Authorised Signatory (Q.M. / T.M.)

Note :

1. The result listed refer only to the tested samples and applicable parameters, Endorsement of product is neither inferred nor implied.
2. Total Liability of our Laboratory is limited to the invoiced amount. No liability will be accepted after the sample is taken back.
3. *Not Covered under NABL Scope.
4. This report can not be used as an evidence in a court of law.
5. Samples will be destroyed after 15 days.
6. Any Complaints about this report should be communicated within 7 days of issue of this report.
7. This report shall not be reproduced except in full, without the written permission of the Laboratory.
8. # Results found outside the range of NABL accredited scope.



TC No : 25

Invoice No: 214

Date : 03-11-2012

Customer Name and Address:

Sara Sae Pvt. Ltd., (Unit-IV)

Behind Radha Swami, Satsang Ghar, G.T. Road, Goraya

Supply condition: As Round

Chemical Analysis

Elements	C	Si	Mn	P	S	Cr	Mo	Ni	Nb	Heat No	Grade	Size	Colour
Result	.053	.44	1.18	.041	.012	16.42	2.03	10.02	.009	T-98	SS316	56mm	Red
Result	.062	.45	1.11	.039	.015	16.45	2.02	10.03	.008	T-99	SS316	56mm	Green
Result	.063	.45	1.17	.043	.015	16.52	2.01	10.03	.012	T-100	SS316	56mm	White
Result	.065	.46	1.17	.041	.014	16.43	2.03	10.06	.013	T-101	SS316	56mm	Pink
Result	.065	.48	1.16	.037	.012	16.64	2.04	10.05	.018	T-102	SS316	56mm	Blue/Green
Result	.061	.46	1.17	.041	.014	16.48	2.02	10.07	.017	T-103	SS316	56mm	Pink/Blue
Result	.054	.43	1.19	.040	.015	16.60	2.05	10.02	.015	U-2	SS316	40mm	Blue
Result	.056	.48	1.17	.041	.017	16.89	2.01	10.02	.019	U-3	SS316	40mm	Pink

Remarks:

1. Manufacturing Route: Induction Furnace
2. Material is free from residual radioactive elements.
3. Lead not added during manufacturing.

We are confirming that test result findings are correct and results are as per standard/customers requirement.


Quality Incharge